



AGS 3506

ART. NO: 3506 | GRAFFITI PROTECTION

AGS 3506 is a pigmented water-carried all-weather long-term protection, formulated for most types of surfaces. **AGS 3506** can be pigmented according to NCS and RAL standards. Protects against graffiti from spray paint, leather dye or marker/felt-tip pen. Protects against graffiti, airborne pollution and moisture for a minimum of 5 years. Permeable and allows protected surface to breathe. Prevents graffiti from penetrating into the surface. A so called sacrificial coating, which means that surface must be re-protected,

INSTRUCTIONS FOR USE

Preparation

Clean off both graffiti and other contamination, such as traffic dirt, wax, oil and paint-residue etc. from the surface. Mask and protect windows in a suitable manner. Ideal temperature for external application should be between 10-35°C. Minimum temperature is +5°C. Relative humidity must not exceed 95%.

Exterior protection

Shake or stir product well prior to use. **AGS 3506** can be applied with an airless sprayer, brush or roller. The protection is applied 2-3 times.

NB! Allow some drying between applications.

AGS 3506 can be applied to a damp, but not wet, surface. Runs and/or excessive application can easily be washed off with water, following completion of work.

Exterior graffiti removal

Method 1 - Normal surface

Remove graffiti with hot water and high-pressure (90°C & 90-150 bar / 1300-2175 PSI). In difficult cases, AGS graffiti removers are used in conventional manner. Re-protect cleaned area.

Method 2 - delicate surface

Apply [AGS 3505](#) with a low-pressure sprayer. Allow a few minutes for the solvent remover to act and then rinse off with hot water (60-90°C & 60-80 bar/870-1160 PSI). The method is most suitable when the surface is brittle. Any graffiti left on the surface can be removed with [AGS 3505](#) on a cloth. The cleaned area should be wiped with a cloth and water. Re-protect cleaned area.

NB! Fresh concrete has to cure for at least 28 days before protection.

Re-protection of cleaned surface

When removing graffiti, the protective coating is also normally removed. Re-protect 2-3 times with **AGS 3506**.

Modified: 2021-11-22

This product information is intended as a guide for use of this product. TRION TENSID AB cannot give any guarantee for end result achieved. Applicator of product shall carry out testing and are responsible for the result.

Dosage

Use as concentrate.

Consumption

Varies depending upon type of surface material. Its porosity and capillary ability etc.

Guidelines

- Concrete, brick or similar, a total consumption for 3 layers will be 0,25-0,3 ltr/m².
- Sandstone, plaster or other soft absorbent surfaces, a total consumption for 3-4 layers will be 0,3-0,4 ltr/m².

Drying-period

The protected surface will be water- and graffiti-resistant after 2 hours and dry after 4 hours. Ultimate protective effect will be achieved after 72 hours.

Storage

Store frost-free in closed original container.

Shelf life

Approximately 12 months in unopened container.

Precautions

Use protective gloves and clothing.

Technical data

- Coloured water-carried wax dispersion.
- Packaging: 10 litre plastic jerricans.
- Density: 1,1 kg/litre.
- Odourless.
- pH-value approx. 8.
- Contains wax, titanium dioxide, alcohols ethoxylated.

Marking

Not classified

Not classified as dangerous goods according to **ADR**.

For more information, see [MSDS](#).

Modified: 2021-11-22

This product information is intended as a guide for use of this product. TRION TENSID AB cannot give any guarantee for end result achieved. Applicator of product shall carry out testing and are responsible for the result.